



EMIST

Licrol A 60

basic fatliquor

Chemical composition	combination of sulphited and sulphated vegetable oils
Active matter	approx. 60 %
Appearance	brown liquid
pH - value (1:10)	6.0 - 8.0
Charge	anionic
Stability	unstable in chrome liquors
Dilution	combinations with other fatliquors have to be stirred thoroughly before dilution, dilution method: 1 : 3 with water of 50 °C – 60 °C

Field of application

Basic fatliquor for all kind of upper leathers.

Properties

- good fullness with tight grain
- waxy touch
- applicable for leathers of all origin

Application

Licrol A 60 should be used in fresh water bath only. The combination with dyestuffs or syntans is not recommended. Licrol A 60 can be used in combination with other anionic or non-ionic fatliquors. Best results are achieved in combination with Licrol SB 114, Licrol SB 124, Licrol SB 154 or Licrol G662.



MADE IN GERMANY

Garment	Licrol A 60 Licrol SB 154 Licrol SB 124	1.0 % - 2.0 % 2.0 % - 3.0 % 2.0 % - 4.0 %
Upholstery	Licrol A 60 Licrol SB 124 Licrol SB 114	1.5 % - 2.0 % 2.0 % - 4.0 % 3.0 % - 5.0 %
Shoe upper	Licrol A 60 Licrol SB 114 Licrol G662	1.0 % - 2.0 % 1.0 % - 2.0 % 1.0 % - 2.0 %

Remark

Licrol A 60 is a technical emulsion and variations in colour and viscosity can happen. The properties for application are not touched by this.



Storage temperature

Storage at temperatures between 5 °C and 40 °C. HEMISTRY



Shelf life

Up to 6 months in the original sealed packing.



Usage Stir before use.

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.