

## Licrol PP

fatliquor for pickle

<b>Chemical composition</b>	blend of synthetic oil and special emulsifiers
<b>Active matter</b>	approx. 50 %
<b>Appearance</b>	whitish to clear microemulsion
<b>pH - value (1:10)</b>	5.0 - 7.0
<b>Charge</b>	anionic
<b>Stability</b>	highly stable to acids and salts under usual tannery conditions, stable in chrome liquors
<b>Dilution</b>	combinations with other fatliquors have to be stirred thoroughly before dilution, dilution method: 1 : 3 with water of 50 °C – 60 °C

### Field of application

Full synthetic multipurpose fatliquor for all kinds of soft and fluffy leathers, as well as fur. Can be used in rewetting of crust and dried wet-blue.

### Properties

- high emulsifying power
- very good electrolyte stability
- even and deep penetration
- good lightfastness
- stabilizes other fatliquors
- outstanding dyeing and leveling properties


### Application

Licrol PP can be used in pickling, tanning and in the main fatliquoring. It is also used in combination with other fatliquors.

Pickle/Chrome tanning	Licrol PP	1.0 % - 2.0 % 2.0 on pelt weight
Chrome retanning	Licrol PP	2.0 % - 4.0 % on shaved weight
Upholstery	Licrol PP	2.0 % - 4.0 % on shaved weight
Garment sheep/goat and suedes	Licrol PP	Up to 10.0 % on shaved weight
In rewetting	Licrol PP	0.5 % - 2.0 % on dried or shaved weight

**Remark**

Licrol PP is a technical emulsion and variations in colour and viscosity can happen. The properties for application are not touched by this.

**Storage temperature**

Storage at temperatures between 5 °C and 40 °C.

**Shelf life**

Up to 6 months in the original sealed packing.

**Usage**

Stir before use.

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.