

Licrol SB 114

semi - synthetic fatliquor

Chemical composition	blend of special natural oils combined with sulphited synthetic oil
Active matter	approx. 50 %
Appearance	yellow oil
pH - value (1:10)	5.0 - 7.0
Charge	anionic
Stability	highly stable to acids and salts under usual tannery conditions, stable in chrome liquors
Dilution	combinations with other fatliquors have to be stirred thoroughly before dilution, dilution method: 1 : 3 with water of 50 °C – 60 °C

Field of application

Multipurpose fatliquor for all kinds of very soft leathers, soft booty nappa, sheep garment nappa, glazed kid and upholstery crusts. Due to its versatile composition Licrol SB 114 can be used as a single fatliquor for all garments and softies.

Properties

- tight grain
- fullness
- light weight
- soft leather with a round and silky handle


Application

Licrol SB 114 can be used alone or in combination with other fatliquors. Combination with Licrol G662 and Licrol L gives a very soft crust. It is very suitable for white crust storage and can also be used as a pre-fatliquor during pickle, chrome tanning, rechroming and in retannage.

Upholstery	Licrol SB 114	6.0 % - 8.0 %
	Licrol PP	1.0 % - 2.0 %
	Licrol PS 7	3.0 % - 6.0 %
Shoe nappa	Licrol SB 114	5.0 % - 8.0 %
	Licrol L	2.0 % - 3.0 %
	Licrol G 662	3.0 % - 6.0 %
Garment nappa	Licrol SB 114	5.0 % - 8.0 %
	Licrol G 662	3.0 % - 5.0 %
	Licrol L	2.0 % - 3.0 %

Remark

Licrol SB 114 is a technical emulsion and variations in colour and viscosity can happen. The properties for application are not touched by this.

**Storage temperature**

Storage at temperatures between 5 °C and 40 °C.

**Shelf life**

Up to 6 months in the original sealed packing.

**Usage**

Stir before use.

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.