



# Licrol SB 126

basic fatliquor

Chemical composition	blend of different types of sulphited fish oils	
Active matter	approx. 60 %	
Appearance	brown transparent oil	
pH - value (1:10)	6.0 - 8.0	
Charge	anionic	
Stability	highly stable to acids and salts under usual tannery conditions, stable in chrome liquors	
Dilution	combinations with other fatliquors have to be stirred thoroughly before dilution, dilution method: 1 : 3 with water of 50 °C – 60 °C	

## **Field of application**

In the chrome tanning and chrome retanning, in the main fatliquoring for soft garment and upholstery leather.

### Properties

- excellent softness LEVER CHEMISTRY
- good fullness and roundness
- only insignificant trend to yellowing
- pleasant odour

## Application

Licrol SB 126 can be added to the chrome tanning and the retanning baths. The combination of Licrol SB 126 and Licrol SB 114 is very suitable for the upholstery, shoe nappa and all kinds of soft leathers.



MADE IN GERMANY

Chrome tannage	Licrol SB 126	0.5 % - 1.0 %
Chrome retannage	Licrol SB 126	1.0 % - 2.0 %
Main fatliquoring for garment and upholstery	Licrol SB 126 Licrol SB 114 Licrol LEC	3.0 % - 4.0 % 5.0 % - 8.0 % 3.0 % - 4.0 %

#### Remark

Licrol SB 126 is a technical emulsion and variations in colour and viscosity can happen. The properties for application are not touched by this.



Storage at temperatures between 5 °C and 40 °C.



#### Shelf life

Up to 6 months in the original sealed packing.



**Usage** Stir before use.

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.