

## Licrol SE

fatliquor additive

<b>Chemical composition</b>	blend of high quality natural oils
<b>Active matter</b>	approx. 100 %
<b>Appearance</b>	light yellow oil
<b>Iodine value</b>	90 ± 10
<b>Saponification value</b>	180 ± 15
<b>Acid value</b>	< 1
<b>Dilution</b>	product is insoluble in water and has to be combined with other water soluble fatliquors, stirred thoroughly before dilution with water, dilution method: 1 : 3 with water of 50 °C – 60 °C

### Field of application

Ideal oil for the replacement of raw sperm oil or neatsfoot oil.

### Properties

- improves the grain resistance and smoothness
- enhances the fullness
- regulates the penetration of other fatliquors
- ideally suited for strong drying of the crust
- very good lightfastness


### Application

Licrol SE has to be combined with other water-soluble fatliquors. Combination of Licrol SE and Licrol K 4, as a top fatliquor, is very suitable for suedes to improve the silky sheen.

Glaze kid	Licrol SE	1.0 % - 2.5 %
	Licrol SB 114	2.0 % - 3.0 %
Heavily retanned chrome leather	Licrol SE	2.0 % - 4.0 %
	Licrol 0598	3.0 % - 5.0 %
	Licrol L	1.0 % - 2.0 %
Softy upper leather	Licrol SE	1.0 % - 2.0 %
	Licrol SB 114	4.0 % - 6.0 %
	Licrol L	2.0 % - 3.0 %
Top fatliquoring	Licrol K 4	0.5 % - 1.0 %
	Licrol SE	0.25 % - 0.5 %

**Remark**

Licrol SE is a technical emulsion and variations in colour and viscosity can happen. The properties for application are not touched by this.

**Storage temperature**

Storage at temperatures between 5 °C and 40 °C.

**Shelf life**

Up to 6 months in the original sealed packing.

**Usage**

Stir before use.

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.