



# **Licrol SG**

main fatliquor

Chemical composition	blend of emulsified natural and synthetic oils	
Active matter	approx. 65 %	
Appearance	white emulsion	
pH - value (1:10)	6.0 - 8.0	
Charge	anionic	
Stability	highly stable to acids and salts under usual tannery conditions, stable in chrome liquors	
Dilution	combinations with other fatliquors have to be stirred thoroughly before dilution, dilution method: 1 : 3 with water of 50 °C – 60 °C	

### **Field of application**

Special fatliquor for suedes and nubucks. It can be used in the main fatliquoring or after fixing in combination with Licrol K 4 for special effects.

### Properties • bea

- ies CLEVER CHEMISTRY
- improves the writing effect
- gives bright colour shades
- very good lightfastness
- gives a full and pleasant handle

## Application

Licrol SG can be used alone or in combination with other anionic or nonionic fatliquors.





Nubuck upper leather	Licrol SG Licrol SB 114 Licrol L	3.0 % - 6.0 % 3.0 % - 6.0 % 1.0 % - 2.0 %
Goat suedes	Licrol SG Licrol SB 154 Licrol LEC	5.0 % - 8.0 % 3.0 % - 5.0 % 2.0 % - 4.0 %
Top fatliquoring	Licrol K 4 Licrol SG	0.5 % 0.5 %

#### Remark

Licrol SG is a technical emulsion and variations in colour and viscosity can happen. The properties for application are not touched by this.



Storage at temperatures between 5 °C and 40 °C.



#### Shelf life

Up to 6 months in the original sealed packing.



Usage Stir before use.

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.