

Licrol SLE

main fatliquor

Chemical composition	blend of sulphited and sulphonated oils with special emulsifiers
Active matter	approx. 40 %
Appearance	beige viscous
pH - value (1:10)	6.0 - 8.0
Charge	anionic
Stability	stable to acids and salts under usual tannery conditions, stable in chrome liquors
Dilution	combinations with other fatliquors have to be stirred thoroughly before dilution, dilution method: 1 : 3 with water of 50 °C – 60 °C

Field of application

Universal fatliquor for all kinds of white and soft, fluffy leathers, Korean nappa, gloving sheep, goat gloving, sheep shoe upper. It can also be used for white leather.

Properties

- very good lightfastness
- soft and fluffy leather
- even and deep penetration
- light weight crust with tight grain
- heat resistant


Application

Licrol SLE can be used in the main fatliquor alone or in combination with other anionic or non-ionic fatliquors.

Glove sheep	Licrol G 662	6.0 % - 8.0 %
	Licrol SLE	4.0 % - 6.0 %
	Licrol PE	3.0 % - 6.0 %
Nappa upper leather	Licrol SLE	3.0 % - 4.0 %
	Licrol L	2.0 % - 3.0 %
Snow white gloves	Licrol SLE	4.0 % - 6.0 %
	Licrol DM 8	6.0 % - 8.0 %

Remark

Licrol SLE is a technical emulsion and variations in colour and viscosity can happen. The properties for application are not touched by this.

**Storage temperature**

Storage at temperatures between 5 °C and 40 °C.

**Shelf life**

Up to 6 months in the original sealed packing.

**Usage**

Stir before use.

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.