



Licrol PS 8

main fatliquor

Chemical composition	blend of sulphited and sulphonated oils, synthetic softeners
Active matter	approx. 50 %
Appearance	beige viscous liquid
pH - value (1:10)	6.0 - 8.0
Charge	anionic
Stability	not stable to acids and salts under usual tannery conditions, not stable in chrome liquors
Dilution	combinations with other fatliquors have to be stirred thoroughly before dilution, dilution method: 1:3 with water of 50 °C – 60 °C

Field of application

Multipurpose fatliquor for all kinds of white, soft and tight grain leather. Especially for the white gloves and white shoe Nappa.

Properties

- very good light fastness
- good bleaching properties
- excellent heat resistance
- waxy touch
- good softness

Application

For the production of all types of white leathers.

ER CHEMISTRY





White gloves	Licrol PS 8	4.0 % - 8.0 %
	Licrol DM 8	4.0 % - 7.0 %
	Ebosoft P 6	2.0 % - 3.0 %
	Licrol SLE	4.0 % - 6.0 %
White shoe upper	Licrol PS 8	3.0 % - 4.0 %
	Licrol DM 8	2.0 % - 3.0 %
White upholstery	Licrol PS 8	4.0 % - 6.0%
	Licrol DM 8	6.0 % - 10.0 %
	Licrol SLE	5.0 % - 8.0 %

Remark

Licrol PS 8 is a technical emulsion and variations in colour and viscosity can happen. The properties for application are not touched by this.



Storage temperature

Storage at temperatures between 5 °C and 40 °C.



Shelf life

Up to 6 months in the original sealed packing.



Usage

Stir before use.

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.