

Ebotan AC

acrylic polymer

Chemical composition	water-soluble acrylic polymer
Active matter	approx. 30 %
Appearance	straw coloured liquid
pH - value (1:10)	6.0 - 8.0
Charge	anionic
Stability	stable to acids and salts under usual tannery conditions
Dilution	1 : 3 with water of 30 °C - 40 °C

Field of application

Anionic retanning agent for chrome tanned and semi-chrome tanned leathers. It is suitable for all kinds of upper leathers, garment as well as for retannage of split suedes.

Properties

- filling and tightening of all types of chrome leathers
- very good buffering properties
- gives suede leathers a soft and silky nap

Application


Ebotan AC may be applied alone or along with vegetable and/or synthetic tannins.

Percentage is based on shaved weight.

Softy and upper leather	Ebotan AC	2.0 % - 5.0 %
Garment cattle	Ebotan AC	3.0 % - 6.0 %
Garment sheep	Ebotan AC	4.0 % - 7.0 %

Remark

Ebotan AC is a technical product and variations in colour and viscosity can happen. The properties for application are not touched by this.

**Storage temperature**

Storage at temperatures between 5 °C and 40 °C.

**Shelf life**

Up to 12 months in the original sealed packing.

**Usage**

Stir before use.

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.