

Ebotan RA 40

retanning agent

Chemical composition	water-soluble acrylic polymer
Solid content	42 %
Appearance	clear, viscous liquid
pH - value (1:10)	6.0 - 8.0
Charge	anionic
Stability	stable to acid and salts under usual tannery conditions.
Dilution	can be added undiluted or 1:3 with water of 30 °C – 40 °C.

Field of application

Retanning agent for all types of leather. It can also be applied in the rechroming.

Properties

- excellent filling properties
- tightening of loose belly and flank areas
- good light fastness and heat resistance
- compatible to all waterproof systems

Application


Ebotan RA 40 is readily water-soluble. It can be directly added to the process or pre-diluted in water.

Percentage is based on shaved weight.

Upper leather	Ebotan RA 40	up to 6.0 %
Softy leather	Ebotan RA 40	up to 4.0 %
Rechroming	Ebotan RA 40	up to 2.0 - 3.0 %

Remark

Ebotan RA 40 is a technical product and variations in colour and viscosity can happen. The properties for application are not touched by this.



Storage temperature

Storage at temperatures between 5 °C and 40 °C. The product is sensitive to frost.



Shelf life

Up to 12 months in the original sealed packing.



Usage

Stir before use.

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.