

Ebotan CLV

tanning/retanning agent

| | |
|-----------------------------|---|
| Chemical composition | sulphonated aromatic condensates |
| Active matter | approx. 95 % |
| Appearance | beige powder |
| pH - value (1:10) | 3.5 - 5.0 |
| Charge | anionic |
| Dilution | can be applied directly to the process vessel |

Field of application

Ebotan CLV is a sulphonated tanning syntan with a low content of monomers. It can be applied for all kind of articles in the retanning and tanning stages.

Properties

- compact fiber structure with even fullness
- good filling properties of the belly
- very fine and tight grain
- excellent lightfastness
- excellent heat resistance

Application


Ebotan CLV can be used together with all other anionic retanning agents.

Percentage based on shaved weight

| | | |
|---------------------|------------|---------------|
| Shoe upper | Ebotan CLV | 7.0 % - 8.0 % |
| Waterproof leathers | Ebotan CLV | 5.0 % - 6.0 % |
| Upholstery | Ebotan CLV | 4.0 % - 5.0 % |

Remark

Ebotan CLV is a technical product and variations in colour can happen. The properties for application are not touched by this.



Storage temperature

Storage at temperatures between 5 °C and 40 °C.



Shelf life

Up to 12 months in the original sealed packing.



Storage

Storage under dry conditions and protected from sun.

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.