

Ebotan MLP

retanning syntan

Chemical composition	condensation product of melamine
Charge	anionic
Active matter	approx. 97 %
Appearance	beige powder
pH-value (1:10)	7.5 – 8.5
Dilution	can be applied directly to the process vessel

Field of application

Ebotan MLP can be used in rechroming, retanning and fatliquoring. It has good selective filling properties while keeping a fine and tight grain structure.

Properties

- very good filling of the loose structures
- fiber tightening properties
- high lightfastness
- good heat resistance
- very low content of free formaldehyde


Application

Percentage is based on shaved weight

Retanning	Ebotan MLP	4.0 % - 6.0 %
Rechroming	Ebotan MLP	2.0 % - 3.0 %
Fatliquoring	Ebotan MLP	1.5 % - 3.0 %

Remark

Ebotan MLP is a technical product and variations in colour can happen. The properties for application are not touched by this.



Storage temperature

Storage at temperatures between 5 °C and 40 °C.



Shelf life

Up to 12 months in the original sealed packing.



Storage

Storage under dry conditions and protected from sun.

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale and Delivery.